

# ELEPHANT ARMOR®

Asphalt Repair & Micro-Trenching Reinstatement Material



## Elephant Armor® Asphalt Repair & Micro-trenching Replacement Material

### DESCRIPTION

Elephant Armor® is a single component, cementitious, fiber based, medium to fast setting, zero polymer, repair and overlay Engineered Ductal Mortar (EDM). In addition to a mechanical bond, our fiber creates a fully engaged molecular bond within our patented mortar matrix, providing extremely high tensile and flexural strength. It can be placed with a textured roller (preferred method) or traditional placement tools.

### FEATURES / BENEFITS:

- Fiber reinforced: Superior flexural and tensile strength as thin as ¼”.
- High ductility, allowing the overlay or repair to ‘FLEX’ without failure.
- Highly resistant to de-icing salts, freeze/thaw.
- Superior tensile strain capacity over other cement based products for improved crack resistance.
- Superior bond strength to that of other fiber and acrylic based mortars.
- Ideal as a structural underlayment.
- Prevents the propagation of existing cracks through the surface.
- Highly impermeable and abrasion resistant.
- Unparalleled as a stampable overlay.

### SHELF LIFE

2 years in original unopened package if stored in a humidity controlled environment. Cannot be exposed to moisture.

### PACKAGING

- 10 lb (4.5 kg) plastic pails
- 50 lb (22.7 kg) plastic lined bags

### COVERAGE/YIELD

A 50 lb (22.7kg) bag of Elephant Armor® Mortar will yield approximately 0.5 ft<sup>3</sup> (0.014 m<sup>3</sup>) of material.

Applied at the following thicknesses, one 50 lb (22.7 kg) bag of Elephant Armor® Mortar will cover:

- ¼” (6.3 mm) – 22 ft<sup>2</sup> (2 m<sup>2</sup>)
- ½” (12.7 mm) – 11 ft<sup>2</sup> (1 m<sup>2</sup>)

Note: Coverage rates are approximate

### PRIMARY APPLICATIONS

Walkways, curbs, ramps, slabs, spalls, cracks, airports-runways, taxiways and gates, bridges, ICF walls, parking structures, tunnels, dams, industrial plants or anywhere a high strength concrete repair mortar is called for. Structural monolithic underlayment or overlay for interior and exterior applications.

## TECHNICAL INFORMATION – Material Properties @ 75°F (24°C)

*All GST material testing properties meet or exceed our published data. Test results are confirmed by third party Independent Laboratories.*

### Compressive Strength psi ASTM C109

- 4 hrs — 4,000 (27.72 MPa)
- 1 day — 5,500 (37.92 MPa)
- 7 days — 6,500 (44.81 MPa)
- 28 days — 7,000 (48.26 MPa)

### Split Tensile Strength psi ASTM C 496

- 28 days — 600 (4.14 MPa)

### Flexural Performance psi ASTM C 1609

- 28 days — 1,600 (11.03 MPa)

### Modulus of Elasticity, ksi ASTM C469

- (ASTM C39 for compressive strength)
- 7 days — 1,800 psi (12.41 MPa)
- 28 days — 2,700 psi (18.62 MPa)

### Shrinkage ASTM C 928/ASTM C157

- 28 days stored in water % — 0.019
- 28 days stored in air % — 0.036

### Electrical Indication of Concrete’s Ability to Resist Chloride Ion Penetration ASTM C 1202

- 321.52 Charge Passed (coulombs)
- Very Low Chloride Ion Penetrability

### Set Times ASTM C 191

- Initial set — approx. 50 min
- Final set — approx. 70 min

### Bond Strength psi ASTM C 882

- 28 days avg — 2500 (17.24 MPa)

### Water-soluble Chloride (% by mass of concrete) ASTM C1218

- 50 days — 0.01391

### Acid-soluble Chloride (% by mass of concrete) ASTM C1152

- 50 days — 0.03087

### Coefficient of Thermal Expansion, in/in/°F AASHTO T-336

- 7 Days — 775
- 28 Days — 4.968 x10<sup>-6</sup>